

Information sheet according to DIN EN 420: General requirements for gloves

**User instructions for Glovebox Gloves**

Type number explanation:

Material	Hand style	Hand size	Material thickness in mm	Hand finish	Cuff diameter in mm	Additional options / styles	Special length in mm
2 = CSM	B= ambidextrous	L=(9-10) XL=(11)	0,4	R = Roughening in Palm		F = F-Type mold G = pre washed S = special length	
	V= fully anatomic		0,6 0,8				

**Cleaning:**

- Cleaning of polluted gloves is best done in lukewarm water and soap solution.
- Do not use chemicals.
- Do not use sharp-edged objects such as wire brushes, sandpaper and similar objects.
- Dry the unsoiled gloves at room temperature.
- If contaminated with chemicals, the gloves are for single use only.

**Storage:**

- Gloves should be stored unbent in a dry and dark environment at a temperature between 5° and 25°C.
- Gloves need to be stored flat with a maximum loading force of 1kg.
- Gloves should never be exposed to direct sunlight.
- To avoid an accelerated aging process, the glove should not be stored in the vicinity of electrical devices in particular near fluorescent tube lamps.
- Recommended shelf life at least 42 months after date of manufacturing, indicated on the glove.

The symbol  on the glove indicates the date of manufacture.

**Handling:**

- The gloves should be checked for any damage before use, damaged gloves should not be used under any circumstances.
- All technical figures relate to as delivered condition, unused and not stretched at room temperature (according to ISO374).
- When using not specified chemicals (not mentioned on the chemical list), please contact your chemical supplier, he will advise you.
- Gloves shall not be worn when there is a risk of entanglement by moving parts of machines

**Type of packaging suitable for transport:**

- Please use a black plastic bag (for example PE) as transport packaging.

**Disposal:**

- Unused, together with normal household waste.
- After contact with chemicals, according to the instructions of the respective chemical disposal.

**Components / Dangerous components:**

- **TU / Thiurame:** This component may be a possible cause of allergies for susceptible persons and consequently lead to skin irritation and / or allergic reactions. In the event of an allergic reaction immediately consult a doctor. Further information is available on request.

**Material characteristics:**

High resistance to oxidizing chemicals, acids, bases, polar organic chemicals and ketones, Temperature range: -20°C to +120°C

**Permeation (permeability):**

The performance level below is based on the breakthrough time determined during a constant contact with the test chemical under normal laboratory conditions, as described in EN 16523-1:2015

Measured breakthrough time	>10 min	>30 min	>60 min	>120 min	>240 min	>480 min
Performance	Level 1	Level 2	Level 3	Level 4	Level 5	Level 6

**Chemical breakthrough time according to DIN EN ISO 374-1: 2017**

Test chemical		Performance Level	
A	Methanol	Level	4
K	Caustic Soda 40%	Level	6
L	Sulfuric Acid 96%	Level	6
P	Hydrogen Peroxide 30%	Level	6

ISO 374-1 / Type B



Information pictogram – Please read the information provided by manufacturer

*Information sheet according to DIN EN 420: General requirements for gloves*

**Please note:** The material thickness is not considered in the permeation test according to EN 16523-1. The tests were therefore performed with glove with the thinnest material thickness. The actual duration of protection at workplace conditions is influenced by many factors such as material thickness, pressure difference, contact with the medium (permanent or intermittent), aging of the material or by negative environmental influences (see storage) and may differ from this performance level!

**Penetration (penetrability) according DIN EN ISO 374-2: 2015: passed**

Penetration resistance was assessed under laboratory conditions and applies only to the samples tested.

**Degradation according DIN EN ISO 374-4: 2014:**

	Test Chemical:	Section	Average value
A	Methanol	Palm	9,7%
A	Methanol	Cuff	1,7%
K	Caustic Soda 40%	Palm	-31,9%
K	Caustic Soda 40%	Cuff	-22,1%
L	Sulfuric Acid 96%	Palm	-17,9%
L	Sulfuric Acid 96%	Cuff	0,8%
P	Hydrogen Peroxide 30%	Palm	-10,3%
P	Hydrogen Peroxide 30%	Cuff	-1,9%

**Remark:** No visually noticeable changes or degradation on the tested areas of the cuff and palm



**Protection against microorganism according DIN EN ISO 374-5: 2017: passed**

Glove for protection against bacteria, fungal infection and viruses.

Penetration resistance was assessed under laboratory conditions and applies only to the samples tested.



**Mechanical characteristics according DIN EN 388:2017 (European Standard)**

	Abrasion resistance	Cut resistance	Tear resistance	Puncture resistance	ISO Cut resistance
Performance	1	1	1	1	X

**Performance level:**

The performance levels for the respective pictogram or for the respective test standard are listed, where:

0: indicates that the glove passed the minimum performance level for a given single hazard;

X: indicates that the test is inapplicable due to glove material or glove design for this glove.

Further information on the performance levels can be found in the corresponding valid standard.

The protective gloves comply with the PPE VO (EU) 2016/425.

**The EU Declaration of Conformity is available at: [www.jung-gt.de](http://www.jung-gt.de) and [www.jugitec.de](http://www.jugitec.de).**

**Safety information:**

This information does not provide information about the actual protection time at the workplace and the distinction between mixtures and pure chemicals.

Resistance to chemicals was evaluated under laboratory conditions on samples taken only from the palm of the hand (except in the case where the glove is 400 mm or longer - in which case the cuff is also tested) and applies only to those tested chemicals. It can be different if the chemical is used in a mixture.

It is recommended to check if the gloves are suitable for the intended use as the workplace conditions may differ from those of the type test depending on temperature, abrasion and degradation.

If protective gloves have already been used, they may offer less resistance to hazardous chemicals due to changes in their physical properties. Degradation, usage, stringing, friction, etc. caused by contact with chemicals can significantly reduce the actual application time. With aggressive chemicals, degradation can be the most important factor to consider when choosing chemical resistant gloves.

Before use, the gloves must be checked for any faults or defects.



Information pictogram – Please read the information provided by manufacturer